

Synthesis And Study Of The Biological Activity Of Nano Schiff Bases Derived From Graphene Oxide

Marwa I Khalil¹, Qadoori Z Khalaf², Atheer A Mahmood³, Khlood A Al-Khafaji²

^{1,2,3}College of Education – Al-Iraqi University / Baghdad- Iraq

⁴Food and Biological Technology Center - Agricultural Research Department -The Ministry of Science and Technology/ Baghdad- Iraq

Email: marwaibrahim2007@outlook.com

Abstract: Novel nanoparticles were prepared by using Schiff's reaction, to produce the nanoparticles Schiff bases (II and III) have been prepared by the composite reaction of graphene oxide and hydrazine hydrate with Isatin and Guanine respectively. On Other hand, Nanoparticle graphene oxide (I) was prepared by using Hummer's method that includes addition of graphite to a mixture of sodium nitrate and concentrated sulfuric acid in the presence of oxidizing agents like potassium permanganate and hydrogen peroxide. The biological activity of the synthesized nanocomposite was studied against various positive and negative gram bacteria by the use of Agar well diffusion method on Mueller - Hinton, the results have shown that the Nano Schiff base II has an interesting inhibition activity especially against the *Staphylococcus aureus* bacteria. On the other hand, Nano Schiff base III has shown moderate activity against *Bacillus thuringiensis* at high concentration of 100 μ L and it exhibits low - zero inhibition activity against other tested bacteria.

Keywords: Nanoparticles; Graphene oxide; Schiff's bases; Isatin, Guanine; drug delivery.

1. INTRODUCTION:

In the last few years, Schiff reaction response presents the most well - know technique for the preparation of many organic compounds. Schiff base derivatives have exhibited a variety of interesting properties [1, 2]. The general protocol of Schiff bases synthesis is often carried out with acid- catalyzed and generally by refluxing the mixture of amine and ketone (or aldehyde) in the organic medium [3-4]. Schiff bases received considerable attention in different areas because of their fascinating synthetic chemical and physical properties [5-8], these proprieties including intermediates on the organic synthesis [9,10], polymer stabilizers [11], dyes and tinctures [12]. Additionally, Schiff bases were possessed various assorted pharmacological enacts like [13, 14] antifungal [15], anti - malarial [16], antibacterial [17], anti - proliferative [18], anti - viral, anti - inflammatory [19] and anti - pyretic properties [20]. The biological activities such as compounds comes from the existence of the azo - methine group (C=N) [21] that have lone - paired of pi electrons in an Sp² hybridized orbital of nitrogen particle [22-23].-

However, Graphene oxide (GO) is a particle with two-dimensional structure and it may be known as a two-dimensional polymer (2D) made up from the covalently bind of oxygen-derivative carbon atoms. It is an exceptional material with superior properties, this is due to its small size and large surface areas [24]. It possesses multiple wonderful attributes characteristics that are originating from its chemical structures composed of various functional groups such as hydroxyl, epoxy, and carboxyl groups and [25]. Because of the low toxicity of graphene oxide and exceptional physical and chemical properties, it gained a widely antimicrobial property [26] and focused on drug delivery [27].

2. MATERIAL AND METHODS

2.1.1- Material

All chemicals Graphite, hydrazine hydrate, Isatin, Guanine, Sodium nitrate, potassium permanganate and hydrogen peroxide got from Fluka and Sigma-Aldrich Co., which were used as received.

2.1.2-Instruments

Fourier-transform infrared spectroscopy (FT-IR) for title compounds were recorded using Shimadzu Fourier Transform WQF-520 Spectrophotometer ($400\text{-}4000\text{ cm}^{-1}$), Baghdad University, Collage of pure Science Ibn-Al-Haitham.

2.1.3- Antibacterial Testing

All equipment's required and bacteria, *Staphylococcus aureus*, *Bacillus thuringiensis* and *Pseudomonas aeruginosa*, formamide (solvent), were acquired from the Ministry of Science and Technology, Industrial Microbiology Department.


2.1.4- Microbiological tests

The microorganisms used to commence microbiological tests are: (1) *Staphylococcus aureus* is Satisfactory bacteria and was isolated from burned skin, (2) *Bacillus thuringiensis* 13 is Ecologic and was isolate from minced meat (3) *Bacillus thuringiensis* 13, (4) *Bacillus thuringiensis* esp., (5) *Bacillus thuringiensis* 3, and (6) *Bacillus thuringiensis* bacteria are Biological Control, (7) *Pseudomonas aeruginosa* 17 which is Environmental bacteria and was isolated from water, finally (8) *Pseudomonas lutilae* 26 that was isolated from the rumen of the camel.

2.2- Synthesis

2.2.1- synthesis of graphene oxide (GO) Nanoparticle (I)


In a suitable 50 ml beaker concentrated sulfuric acid (23 ml) was added and placed in an ice-bath to reduce the homogeneity of the temperature, then (0.5 g, 0.005 mole) of sodium nitrate was added gradually for about 15 minutes with constant stirring. After that, (0.2 g) of graphite dust (G) was added step by step for 10 minutes with continuous stirring. (3 g, 0.021 mole) of potassium permanganate which was added for about 15 minutes with stirring. The mixture left in an ice-bath for 5 minutes, then it was stirred at room temperature at $25\text{ }^{\circ}\text{C}$ for 60 minutes. After that (46 ml) of distilled water dropped for 20 minutes, warm water (140 ml) added and the mixture left to stir for period 10 minutes, then (9 ml) of hydrogen peroxide 30% added with continued stirring for 30 minutes. The mixture was cooled and filtered with special filter paper and washed with distilled water ($3 * 5\text{ ml}$), dried at a temperature of $60\text{-}70\text{ }^{\circ}\text{C}$ until the weight is stable (4 hours). (Scheme-1) Percentage of compound was 85 % with Black color.



Scheme 1- synthesis of graphene oxide (GO) Nanoparticle (I) by Hummer's method from graphite

2.2.2- Synthesis of Nano Schiff bases II and III

Graphene oxide (0.1 g) mixed with (2mL) of hydrazine hydrated 80% (without solvent), then the mixture was put on soil-bath until the color and the nature of compound changed. After that, (0.1 g) of isatin, guanine was added respectively. The mixture heated in mental until the color and the texture of the synthesized nanoparticle was changed. The nanocomposites (**II** and **III**) were recrystallized from ethanol (Scheme 2) Yield (%) and Colors for the synthesized nanoparticles was 70 and 75 and pale gray.



Scheme 2- Synthesis of Nano Schiff particles II and III particles by composite method

2.2.3- Antimicrobial activity of Nano particles

The antimicrobial activity of nanoparticles was determined by using the agar well diffusion method on Mueller-Hinton agar [28]. Sterilized medium Muller Hinton agar was cooled to

about (50 ± 2 °C), then it was poured into petri-dish and allowed to gel firmly before inoculating by bacterial species. Bacterial cultures of *Staphylococcus aureus*, *Bacillus thuringiensis*, and *Pseudomonas aeruginosa*, were used as challenge specimens. Bacterial cultures were crashed out from the nutrient agar plate and suspended in sterilized peptone water. McFarland standard tube number 1 was applied for bacterial turbidity evaluation; it equivalents approximately amounts to (1×10^8 CFU/mL). A cotton swab was immersed in the bacterial suspension and spread over Muller Hinton agar which let stand for about 10 min to ensure bacterial adherence. Meanwhile, the borer applicator was sterilized by flame, cooled, and pressed on the top of seeded Muller Hinton agar to make a well with a 7 mm radius. Distances were kept away between wells because of the aspect of the plate. Each well was filled with 100, 50, and 25 μ L of a solution containing nanoparticles; control wells were filled with 100, 50, and 25 μ L of formamide. Plates were left for 10 minutes, in the laboratory and then were incubated for 24 h at 37 °C. Three replicas of each plate were prepared and the diameter of the inhibition zone was recorded from the edge of the well to the end of the halo zone. The inhibition zone was measured in mm (Diagram 1 and 2).




Diagram-1 This figure shows the inhibition zone of Nano Schiff base II against the tested bacteria in different concentrations 100, 50, and 25 μ L




Diagram-2 This figure shows the inhibition zone of Nano Schiff base III against the tested bacteria in different concentrations 100, 50, and 25 μ L

3- Results and discussion

3.1- FTIR analysis

FT-IR of the synthesized nanoparticles (**I –III**) were recorded in KBr medium in the spectral range (4000–500) cm^{-1} . Graphene oxide (GO) was synthesized by using Hummers' method without any alteration [29], the mechanism of the reaction was shown in (Scheme-1). FT-IR of nanoparticle GO I (Figure-1) showed a broad absorption band at (3200-3300) cm^{-1} due to the overlapping of ν (O-H str.) of carboxylic and alcohol groups. Another absorption band was at (1650-1670) cm^{-1} for the overlapping ν (C=O str.) of carboxylic and ketones groups, stretching band at 1200 cm^{-1} due to ν (C-OH str.) and stretching band at 1060 cm^{-1} attributed to ν (C-O str.) of epoxy groups.




Figure 1- The FT-IR spectrum [1] graphite (G) and [2] graphene oxide I (GO)

FTIR spectrum of nanoparticle compound II (Figure-2) had shown a number of IR absorption bands 1730 cm^{-1} for ν (C=O str.) of five-member isatine ring, 1618 cm^{-1} for ν (C=N str.) group, stretching vibration occurs at (3192-3109) cm^{-1} assignable to ν (NH str.), bands at 3060-3041 cm^{-1} for ν (C-H str.) of aromatic, sharp band at 1462 cm^{-1} due to ν (C=C str.). A stretching band was at 3446 cm^{-1} due to the overlapping of OH carboxylic and hydroxyl groups of GO. The FTIR of nanoparticle III (Figure- 3) showed a new sharp band at 1697 cm^{-1} which was attributed to ν (C=O str.) of six-member purine ring, stretching band at 1674 cm^{-1} due to carbonyl groups for carboxylic acid and ketones. Another stretching bands were at 1560 cm^{-1} for ν (C=N str.), (1473-1417) cm^{-1} for ν (C=C str.) aromatic groups. It was observed that a broad band of (3113-3170) cm^{-1} was assigned to ν (NH, NH₂ str.). Broadband at 3327 cm^{-1} was due to the overlapping of O-H stretching vibration for both carboxylic and hydroxyl groups of GO. A bands at (2991- 2906) cm^{-1} due to the ν (C-H str.) of aromatic.




Figure 2- The FTIR spectrum of Nano particle (II)




Figure 3- The FT-IR spectrum of Nano particle (III)

3.2- Antibacterial activity

The microbial activity of the nanoparticles Schiff bases (II and III) were tested in vitro by using several types of bacteria and using the agar well diffusion method. The tested bacteria were Pathological and Environmental isolates. The nanocomposites exhibited different bioactivity ranging from (high, medium, and low) effect. The biological activity was examined by using different concentrations (25, 50, and 100 μ L) and types of bacteria to increase the chance of detecting antibiotic principles in tested materials. The results of the bactericidal examination are listed in Tables 1 and 2. In this paper, we used GO as drug delivery [30]. The effect of the nanoparticle Schiff base II in the anti-bacterial activity against the tested Gram (+ve) and Gram (-ve) organism's exhibits that the synthesized nano Schiff base can be used in treating the bacteria associated with burns as well as its activity against environmental bacteria that used extensively in biological control program against insects. A reason was given for an active presence of imine groups, also due to p-electron delocalization, on the whole, the nanoparticles that affected

This figure shows the antibacterial activity of Nanoparticle (II) against tested bacteria in 100, 50 and 25 μ L



Figure 4- This figure shows the antibacterial activity of Nanoparticle (II) against tested bacteria in 100, 50 and 25 μL

Furthermore, the synthesized Nano Schiff base III was found to have moderate activity against *Staphylococcus aureus* only at high concentration 100 μL and low action against *Bacillus thuringiensis* at concentration 100 μL , which indicated for dose dependent activity of nano Schiff base II as presented in (Figure-5).




Figure 5- This figure shows the antibacterial activity of Nanoparticle (III) against the tested bacteria in 100, 50 and 25 μL

Table 1- The in vitro anti - bacterial activity of Nano Schiff base compound II, inhibition zone (mm)

Tested Bacteria	Concentration 100 μL	Concentration 50 μL	Concentration 25 μL
<i>Staphylococcus aureus</i>	11.5	9.5	4.5
<i>Bacillus thuringiensis</i> 13	6.5	4.5	1.5
<i>Bacillus thuringiensis</i> esp.	2.5	9	1.5
<i>Bacillus thuringiensis</i> 3	2.5	1.5	1
<i>Bacillus thuringiensis</i>	10.5	3.5	1.5
<i>Pseudomonas aeruginosa</i>	10	8	7.5

17			
<i>Staphylococcus aureus</i>	10	5	4
<i>Pseudomonas lutellae</i> 26	11.5	6.5	4

Table 2- The in vitro anti – bacterial activity of Nano Schiff base compound III, inhibition zone (mm).

Tested Bacteria	Concentration 100µL	Concentration 50 µL	Concentration 25 µL
<i>taphylococcus aureus</i>	3	2	-
<i>taphylococcus aureus</i>	-	-	-
<i>acillus thyuringiensis</i> 13	4	1	-
<i>acillus thyuringiensis</i> esp.	-	-	-
<i>acillus thyuringiensis</i> 3	2	1	1
<i>acillus thyuringiensis</i>	3	2	1
<i>seudomonas aeruginosa</i> 17	-	-	-
<i>seudomonas Iutllae</i> 26	-	-	-

µL = Microliters, (-)= no inhibition

3. CONCLUSION

In this paper, we reported the preparation of the nanocomposites by using the Schiff's reaction which has been diagnosed by using FT-IR technology. The biological activity was studied for the nanocomposites on different types of bacteria. We concluded that the

nanocomposite II that was prepared from the combination reaction of graphene oxide and Isatin has a wide range of inhibition for gram positive bacteria and gram negative bacterial species. Moreover, nanocomposite III has a low bacterial inhibition capacity comparing with the first nanoparticle. In the future, we believe that it is possible to use nanoparticle II as an ointment to treat *S. aureus* that extensively associated with infections of burn especially with long period of hospitalized patients. Graphene oxide (GO) possesses multi properties that make it more attractive for biomedical applications and it can be used as a therapeutic delivery. Finally, the main reason for the effort is due to the unique effect of the nanocomposites as bacterial inhibitors which could provide usefulness in biomedicine and therapy.

Acknowledgements

We extend our sincere thanks and appreciation to the Department of Chemistry- College of Education, Al-Iraqi University due to support and encouragement. Our gratitude is due to the Industrial Microbiology Department, Ministry of Industry, and Minerals for their help in completing the part of the biological study of the research. Also, their thanks go to the College of Education for Pure Sciences Ibn Al-Haitham, University of Baghdad, for achieving the FT-IR spectrums.

REFERENCES

- [1] Singh, P., Goel, R. L., and Singh, B. P. **1975**. Synthesis, Characterization and Biological Activity of Schiff Bases, *J. Indian Chem. Soc.*, **52**:958-970.
- [2] Patai, S. **1970**. The Chemistry of Carbon–Nitrogen Double Bond. New York. John Wiley & Sons Ltd.
- [3] Kalaivani, S., Priya, N., and Arunachalam, S. **2012**. Schiff bases: facile synthesis, spectral characterization and biocidal studies. *Inter.J. Appl.Bio. Pharm.Tachnol*, **3**:219–223.
- [4] Souza, P., Garcia-Vazquez, J. and Masaguer, J. R. **1985**. Synthesis and characterization of copper(II) and nickel(II) complexes of the Schiff base derived from 2-(2-aminophenyl) Benz imidazole and salicylaldehyde. *Transition Met. Chem.* **10**:410–412. doi.org/10.1007/BF0109674
- [5] Ashraf, M., Mahmood, K., and Wajid, A. **2011**. Synthesis, Characterization and Biological Activity of Schiff Bases. *IPCBE*, **10**:1–7.
- [6] H. Schi, “Mittheilungen aus dem Universit
- [7] atslaboratorium in
- [8] Pisa: eine neue reihe organischer Basen,” *Justus Liebigs Annalen*
- [9] der Chemie, vol. ,no. ,pp. – ,
- [10] Brodowska, K., and Chruscinska, E. L. **2014**. Schiff bases – interesting range of applications in various fields of science. *CHEMIK*, **68**:129–134.
- [11] Ashraf, M., Wajid, A., Mahmood, K., Maah, M. and Yusoff, I. **2011**. Spectral Investigation of the Activities of Amino Substituted Bases. *Orient. J. Chem*, **27**:363–37. <http://www.orientjchem.org/?p=11666>
- [12] Al Zoubidi, W. **2013**. Solvent extraction of metal ions by use of Schiff bases. *J. Coord. Chem*, **66**:2264-2289. <https://doi.org/10.1080/00958972.2013.803536>
- [13] Atwood, D. A. **1997**. Salan complexes of the group 12, 13 and 14 elements. *Coord. Chem. Rev.*, **165**:267-296. [https://doi.org/10.1016/S0010-8545\(97\)90159-4](https://doi.org/10.1016/S0010-8545(97)90159-4)
- [14] Shibuya, Y., Nabari, K., Kondo, M., Yasue, M., Maedo, K., Uchida, F., and Kawaguchi, H. **2008**. The Copper(II) Complex with Two Didentate Schiff Base

- Ligands. The Unique Rearrangement that Proceeds under Alcohol Vapor in the Solid State to Construct Non-inclusion Structure. *Chem. Lett*, **37**:78. <https://doi.org/10.1246/cl.2008>
- [16] Al Zoubi, W., Ali Salih, A., Duraid, S. and Gun Ko, Y. **2017**. A new Azo-Schiff base: Synthesis, characterization, biological activity and theoretical studies of its complexes. *Appl. Organometal. Chem*, **12**: 1-15 . <https://doi.org/10.1002/aoc.3895>
- [17] Asadi, M., Sadi, B., Asadi, Zo j., Yousefi, R., Barzegar, A. and Hezarjaribi, K. **2012**. Synthesis, characterization and the interaction of some new water-soluble metal Schiff base complexes with human serum albumin. *J. Coord. Chem*, **65**:722-739. <https://doi.org/10.1016/j.saa.2013.10.070>
- [18] Rice, L. **1972**. Unmet medical needs in antibacterial therapy. *J. Biochem. Pharmacol*, **71**:991–995, <https://doi.org/10.1016/j.bcp.2005.09.018>
- [19] Williams, D. R. **1972**. Metals, ligands, and Cancer. *Chem. Rev*, **72**:203–213. <https://doi.org/10.1021/cr60277a001>
- [20] Sari, N., Arslan, S., Logoglu, D. R., and Sakiyan, I. **2003**. Antibacterial activities of some new amino Acid-Schiff bases. *G.U.J. Sci.*, **16** :283-288.
- [21] Sakthivel, A., Thalavaipandian, A., Raman, N., and Thangagiri, B. **2017**. Synthesis, characterization and Antifungal activity of transition metal (II) complexes of Schiff base derived from p-amino acetanilide and salicylaldehyde. *IP Indexing - Impact factor*, **3**: 1253-1260. <https://doi.org/10.1080/07391102.2020.1801508>
- [22] Kolochi, T., Victoria, A. and Elangovan, N. **2016**. Antibacterial and antifungal activities of derivatives of 4-amino salicylic acid. *Chem. Pharm. Res*, **8**:782-785.
- [23] Singh, D.P., Kumar, K. and Sharma, C. **2009**. Antimicrobial active macrocyclic complexes of Cr (III), Mn (III) and Fe (III) with their spectroscopic approach. *Eur. J. Med. Chem*, **44**: 3299-330. <https://doi.org/10.1016/j.ejmech.2009.02.029>
- [24] Bagihalli, G., Avaji, P., Patil, S. and Badami, P. **2008**. Synthesis, spectral characterization, in vitro antibacterial, antifungal and cytotoxic activities of Co(II), Ni(II) and Cu(II) complexes with 1,2,4-triazole Schiff bases. *Eur. J. Med. Chem*, **43**: 2639-2649. <https://doi.org/10.1080/14756360802187901>
- [25] Chaviara, A., Cox, P., Repana, K., Papi, R., Papazisis, K., Zambouli, D., Kortsaris, A., Kyriakidis, D. and Bolos, K. **2014**. Copper (II) Schiff base coordination compounds of dien with heterocyclic aldehydes and 2-amino-5-methyl-thiazole: synthesis, characterization, anti-proliferative and antibacterial studies. Crystal structure of CudienOOC₂. *J. Inorg. Biochem*, **98**:1271-1283. <https://doi.org/10.1016/j.jinorgbio.2004.05.010>
- [26] Li, L., Chen, K., Yu, H. Ma. R. and Liu, D. **1999**. Investigation on some Schiff bases as HCl corrosion inhibitors for copper. *J. Corros. Sci*, **41**: 1273-1287. [https://doi.org/10.1016/S0010-938X\(98\)00183-8](https://doi.org/10.1016/S0010-938X(98)00183-8)
- [27] Chakraborti, A.K., Bhagat, S., Rudrawar, S. **2004**. Magnesium perchlorate as an efficient catalyst for the synthesis of imines and phenylhydrazones. *Tetrahedron Lett*, **45**: 7641-7644.
- [28] Valcarcel, M. and Laque de Castro, M. D. **1994**. Flow-Through Biochemical Sensors. Amsterdam. Elsevier Science.
- [29] Priyadarsini, S., Mohanty, S., Basu, S. and Mishra, M. **2018**. Graphene and graphene oxide as nanomaterials for medicine and biology application, *J. Nano. Chem*, **8**:123–137, <https://doi.org/10.1007/s40097-018-0265-6>
- [30] Rostamizadeh, S., Hemmasi, A. and ZekriMagnetic, N. **2017**. Amine-functionalized graphene oxide as a novel and recyclable functional Nano catalyst for solvent-free

- synthesis of pyrano [3,2-c] pyridine derivatives. *Nano chem. Res*, **2**: 29-41, <https://doi.org/10.22036/NCR.2017.01.004>
- [32] Ghuge, A., Shirode, R. and Kadam, V. **2017**. Graphene: a comprehensive review. *Curr. Drug Targets*, **18**: 724–733. <https://doi.org/10.2174/1389450117666160709023425>
- [33] Cheng, C., Li, S., Thomas, A., Kotov, N. A. and Haag, R.**2017**. Functional graphene nanomaterials based architectures: bio interactions, fabrications, and emerging biological applications. *Chem. Rev*, **117**: 1826-1914. <https://doi.org/10.1021/acs.chemrev.6b00520>
- A. Bauer, W. Kirby, J. Sherris, M. Turk, Antibiotic susceptibility testing by a standardized single disk method, *Am J. Clin. Pathol.*45 (1966) 493-499.
- [34] Alhayani B., H. Ilhan.(2020). “Image transmission over decode and forward based cooperative wireless multimedia sensor networks for Rayleigh fading channels in medical internet of things (MIoT) for remote health-care and health communication monitoring,” *Journal of Medical Imaging And Health Informatics*, vol. 10, pp. 160-168.
- [35] Alhayani B.,H.Ilhan. (2020). Efficient cooperative image transmission in one-Way multi-hop sensor network,” *International Journal of Electrical Engineering Education*, vol.57, no.2, pp.321-339
- [36] Alhayani, B. and Abdallah, A.A. (2020), "Manufacturing intelligent Corvus corone module for a secured two way image transmission under WSN", *Engineering Computations*, Vol. 37 No. 9, pp. 1-17.
- [37] Alhayani, H. Ilhan, (2017). “Hyper spectral image classification using dimensionality reduction techniques”, *International Journal of Innovative Research in Electrical, Electronics, Instrumentation and Control Engineering*,, vol.5, pp.71-74.
- [38] Alhayani, Milind Rane. (2014). ”face recognition system by image processing” *International journal of electronics and communication engineering & technology (IJCIET)*,vol.5, no.5, pp. 80–90.
- [39] B. Al-Hayani, H. Ilhan. (2020)“Visual Sensor Intelligent Module Based Image Transmission in Industrial Manufacturing for Monitoring and Manipulation problems,” *Journal of Intelligent Manufacturing*, vol.4,pp.1-